

Product Specification
Ground Granulated Blast Furnace Slag

Chemical Analysis	
Element	Value
SiO ₂	36.00
Al ₂ O ₃	15.50
Fe ₂ O ₃	1.15
CaO	38.00
MgO	8.70
SO ₃	0.50
K ₂ O	0.50
Na ₂ O	0.50
Cl	0.020
S-2	1.30
Mn ₂ O ₃	1.50
TiO ₂	1.40
L.O.I	0.25
I.R	0.50

Physical Analysis	
Element	Value
Blaine	4000
Residue on sieve 200μ	<0.20
Residue on sieve 90μ	<2.00

Note: This a typical specification. For your order, we'll send the specific one.

Code: Arij-GBFS-SPH-701